

## LOW CIS-1.4-POLYBUTADIENE RUBBER (BR) 277

### Manufacturer

Dushanzi Petrochemical Company

### Applications

It is a synthetic rubber for its good cold resistance, abrasion resistance, anti-aging resistance, low heat generation and high elasticity. It is used to mix with natural rubber to produce tyre tread, conveying belts, coated fabrics and soles.

### Package, storage and transportation:

The product is packed in composite paper-plastic bags lined with polyethylene film. The net unit weight is 25kg . It should be stored in cool, clean, dry and well-ventilated warehouse. Outdoor storage and direct sunlight should be prevented. Protect from sun, rain, damage and contamination during transportation.

### Specifiatiion:

Item	The quality index		Test method
	BR277		
Volatiles, % ≤	0.7		Q/SY DS 0523
Ash, % ≤	0.2		Q/SY DS 0526
Raw rubber Mooney viscosity, ML(1+4) 100℃≤	37-47		Q/SY DS 0522
Oil % (m/m)	26.3-29.3		Q/SY DS 0525
Vingl, %(m/m) 1.3-butadiene)	11-13		Q/SY DS 0520
Note: It is achromaticity or tint block rubber.			